

What is claimed is:

1. A polyamide resin composition comprising 100 parts by weight of a polyamide resin component (A) and 0.01 to 5 parts by weight of a metallic soap component
5 (B), wherein:
the polyamide resin component (A) comprises:
a dicarboxylic acid component (a-1), which comprises a terephthalic acid component, and an aromatic dicarboxylic acid component other than the terephthalic
10 acid component and/or an aliphatic dicarboxylic acid component of 4 to 20 carbon atoms, and
a diamine component (a-2) comprising an aliphatic diamine component; and
the metallic soap component (B) comprises a metallic
15 soap comprising an aliphatic carboxylic acid of 20 to 25 carbon atoms and a monovalent or divalent metal salt.
2. The polyamide resin composition as claimed in claim 1, wherein the polyamide resin component (A) has an
20 intrinsic viscosity, as measured in 96.5% sulfuric acid at 25°C, of 0.5 to 3.0 dl/g and a melting point, as measured by a differential scanning calorimeter (DSC), of 280 to 330°C.

3. The polyamide resin composition as claimed in claim 1 or claim 2, which further contains a filler in an amount of 1 to 300 parts by weight based on 100 parts by weight of the polyamide resin component (A).

5

4. The polyamide resin composition as claimed in claim 3, wherein the filler comprises a glass fiber, a flame retardant, a flame retarding assistant and a lubricant.

10

5. A molded article comprising the polyamide resin composition of any one of claims 1 to 4.